Note: This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.

TÜV SUD

PSB Singapore

Add value. Inspire trust.

SUBJECT

Testing of Gloves

CLIENT

Shijiazhuang Hongray Group Co.,Ltd. South Tongda Rd., East Dist., Jinzhou City, Hebei, 052260, China

SAMPLE SUBMISSION DATE

08 Nov 2021

TEST DATE

10 Nov 2021 to 13 Dec 2021, 24 Dec 2021

DESCRIPTION OF SAMPLES

S/N	Product Description	Brand/ Model	Colour	Product Code	Size	Sample Received (pieces)	Manufacturer
1		/	A 211		XS	400	
2	Disposable Nitrile	16		NDE 4004	S	400	Shijiazhuang
3	Examination Gloves	Hongray	Black	NPF4001- 4005	М	400	Hongray Group
4	(Black, Powder Free)			4000	L	400	Co.,Ltd.
5					XL	400	

Lot size as specified by client: 150,001 to 500,000 pieces per lot

METHOD OF TEST

- EN 455-1:2020 Medical gloves for single use Part 1: Requirements and testing for freedom from holes
- EN 455-2:2015 Medical gloves for single use Part 2: Requirements and testing for physical properties
- 3. EN 455-3:2015 Medical glove for single use Part 3: Requirements and testing for biological evaluation



Laboratory: TÜV SÜD PSB Pte. Ltd. 15 International Business Park TÜV SÜD @ IBP Singapore 609937 Phone: +65-6778 7777 E-mail: info.sg@tuvsud.com https://www.tuvsud.com/sg Co. Reg: 199002667R Regional Head Office: TÜV SÜD Asia Pacific Pte. Ltd. 15 International Business Park TÜV SÜD @ IBP Singapore 609937



RESULTS

Sample: Disposable Nitrile Examination Gloves (Black, Powder Free), Hongray, NPF4001-4005

Table 1: Results for EN 455-1:2020

Clause	Tests	Size	Requirements	No. of non-compliers allowed (pieces)	Number tested (pieces)	Actual no. of non-compliers found (pieces)	Inferred results
4 5	Freedom from holes	XS	Shall not leak	10	315	0	Passed
		S		10	315	0	Passed
		М		10	315	0	Passed
		L		10	315	3	Passed
		XL		10	315	0	Passed

Table 2: Results for EN 455-2:2015 Clauses 4-5

Clause	Tests	Size	Requirements (Median)	Number tested (pieces)	Results (Median)	Inferred results
	Dimensions a) Length (mm)	XS		13	240	Passed
		S		13	241	Passed
		М	≥ 240	13	243	Passed
		L		13	247	Passed
4		XL		13	249	Passed
4		XS	≤ 80	13	80	Passed
	b) Width (mm)	S	80 ± 10	13	83	Passed
		М	95 ± 10	13	97	Passed
		L.	110 ± 10	13	103	Passed
		XL	≥ 110	13	114	Passed
	Strength a) Force at break (N)	XS	1100	13	10.4	Passed
		S	For nitrile	13	7.5	Passed
5		orce at break M examination	examination	13	7.6	Passed
		L	9.6vcs. ≥ 6.0	13	7.6	Passed
		XL	7	13	6.3	Passed
	b) Force at break after challenge testing (N) 7 days at	XS		13	9.0	Passed
		S	For nitrile examination gloves: ≥ 6.0	13	7.3	Passed
		М		13	7.5	Passed
		L		13	7.5	Passed
	(70±2)°C	XL		13	6.4	Passed

Table 3: Results for EN 455-2:2015 Clause 7

Clause	Tests	Requirements	Results	Inferred results
7	Labelling	Manufacturers shall label the glove and/or the packaging with the date of manufacture in accordance with EN ISO 15223-1:2012 and EN 1041:2008+A1:2013. Date of manufacture is defined as the packaging date.	Observed	Passed



RESULTS (cont'd)

Sample: Disposable Nitrile Examination Gloves (Black, Powder Free), Hongray, NPF4001-4005

Table 4: Results for EN 455-3:2015 Clauses 4.2-4.5

Clause	Tests	Requirements	Results / Remarks	Inferred results
4.2	Chemicals	Gloves shall not be dressed with talcum powder (magnesium silicate).	Glove is not dressed with talcum powder, based on client's declaration letter	Passed
		Other chemicals	Manufacturer shall disclose upon request a list of chemical ingredients	NA
4.3 5.1	Endotoxins	< 20 EU/pair for gloves labelled with 'low endotoxin content'.	Not labelled with 'low endotoxin content'	NA
			XS 0.11 mg per glove	Passed
	Powder- free gloves	For powder-free gloves: The total	S 0.10 mg per glove	Passed
4.4 5.2		duantity of nowder residues shall not	M 0.07 mg per glove	Passed
5.2			L 0.03 mg per glove	Passed
			XL 0.18 mg per glove	Passed
4.5 5.3	Proteins, leachable	The manufacturer shall strive to minimize the leachable protein level for gloves containing natural rubber latex.	Not natural rubber latex glove	NA

Table 5: Results for EN 455-3:2015 Clause 4.6

Clause	Tests	Requirements	Results
	Labelling	In addition to the labelling specified in EN 1041:2008+A1:2013 and the relevant symbols given in EN ISO 15223-1:2012, the following requirements apply: a) medical gloves containing natural rubber latex shall be labelled on the packaging of at least the smallest packaging unit with the EN	NA
		ISO 15223-1:2012 symbol for latex; The labelling shall include the following or equivalent warning statement together with the symbol: '(Product) contains natural rubber latex which may cause allergic reactions, including anaphylactic responses';	NA
4.6		 b) the labelling shall include a prominent indication of whether the glove is powdered or powder-free; 	Comply
		 c) sterile powdered gloves shall be labelled with the following or equivalent: 'CAUTION: Surface powder shall be removed aseptically prior to undertaking operative procedures in order to minimize the risk of adverse tissue reactions'; 	NA
		 d) for any medical glove containing natural rubber latex the product labelling shall not include: - any term suggesting relative safety, such as low allergenicity, hypoallergenicity or low protein; - any unjustified indication of the presence of allergens; 	NA
		e) if the manufacturer labels the gloves with the protein content, the process limit, measured as specified in 5.3 shall be given.	NA
		Inferred results	Passed



REMARKS

- Labelling requirements are assessed based on submitted packaging artwork by client on 23 Dec 2021.
 NA: Not applicable for the submitted sample.

eo Poh Kwang Associate Engineer

Wong Bee Hui Product Manager Medical Health Services (NAM)





APPENDIX



Photo 1: Disposable Nitrile Examination Gloves (Black, Powder Free), Hongray, NPF4001-4005



Photo 2: Packaging artwork for Disposable Nitrile Examination Gloves (Black, Powder Free), Hongray, NPF4001-4005



Please note that this Report is issued under the following terms :

- 1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
- The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
- 3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
- 4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
- Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, 15 International Business Park TÜV SÜD @ IBP Singapore 609937.
- 6. The tests carried out by TÜV SÜD PSB and this report are subject to TÜV SÜD PSB's General Terms and Conditions of Business and the Testing and Certification Regulations of the TÜV SÜD Group.

